

Test Report

Date: July 28, 2010

Page 1 of 2

The following sample(s) was/were submitted and identified by/on behalf of the client as: STAINLESS STEEL WATER BOTTLE WHITE COLOR EXTERIOR PART

Style/Item No.

: STRAW LID TYPE

Supplier

: PHOTO USA

Country of Origin

: CHINA

Sample Receiving Date

: July 22, 2010

Testing Period

: July 22 to July 28, 2010

Test Requested

: (1) To determine extractable lead and cadmium contents of exterior

decorations of the submitted sample with reference to Superior Court of the State of California - County of San Francisco Case No CGC 04- 436729 and

No.CGC-003-418025.

Test Method

: (1) With reference to Superior Court of the State of California - County of San Francisco Case No. CGC-04-436729 Exhibit B Testing Protocol. Analysis was performed by AAS.

Signed for and on behalf of SĞS-CSTC Chemical Laboratory

Lubora

Reabeca Zhou Approved Signatory

ent is accord by the Congany subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.aga.con/terms.end.conditions. elseyberic format documents.subject to Terms and Conditions for Electronic Documents at www.aga.com/terms.e-document.him. Attention is drawn to the imitation of spatial but and jurisdiction issues defined therein. Any holder of this focument is advised that information contained herein reflects the Company's little instructions, the first him to the initial of Clean's instructions, the first. He Company's cole responsibility is to its Client and this document contained herein reflects the Company is not responsible to the first and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Only of the first of the Company. Only of the Company of the Company of the Company.



Test Report Date: July 28, 2010 Page 2 of 2

Test Results :

1) Exterior decorations

Leachable Lead and Cadmium Content

Silver grey metal bottle with white coating (lid excluded)	<u>Extract</u> <u>Volume (ml)</u>	<u>Internal</u> <u>Volume (ml)</u>	<u>Lead</u> (ppm)	Cadmium (ppm)
1	900	650	< 0.1	< 0.01
2	900	650	< 0.1	< 0.01
3	900	650	< 0.1	< 0.01
4	900	650	< 0.1	< 0.01
5	900	650	< 0.1	< 0.01
6	900	650	< 0.1	< 0.01
Maximum Permissible Limit (California Prop 65) for Ceramic			0.99	0.049
Maximum Permissible Limit (California Prop 65) for Glass			1.5	0.049
Maximum Permissible Limit (California Prop 65) for Others			0.1	0.049

Note

- 1. ppm = microgram per millitre relative to the internal volume of the tested sample.
- 2. <= less than
- 3. The maximum permissible limit is quoted from Superior Court of the State of California -County of San Francisco Case No CGC 04- 436729 and No CGC-003-418025 and it is applicable for Pottery (ceramics)/Glass product only, but not for other kind of products such as metal.

Sample photo:



SGS authenticate the photo on original report only *** End of Report **

art is saided by the Company subject to the General Conditions for Electronic Documents at weaking on request or accessible at HID Www.aps.com/arms_arms_conditions_ electronic format documents_autiject by Terms and Conditions for Electronic Documents at weakings com/arms_endocument/lim. Attention is drawn to the Endledian of any Conditions of the Company, in this posturement is advised that information contained hereon referred the Company is Influenced at the time of on only large to the the interior of Client and this document code not contained particle to a transaction of any the Company is the contained the Company in the C